Color Stain[™] 250 System

SYSTEM DATASHEET

SYSTEM DESCRIPTION

A water-based, penetrating, acrylic/urethane stain sealer with a two component, high-performance, ultra violet light stable, low viscosity, acrylic aliphatic urethane primer/sealer polyester urethane top coat. S-9500 Color Stain is translucent stain available in 20 standard colors, and provides a natural, fresh look for old as well as new surfaces, interior and exterior.

FEATURES & BENEFITS

- Simple application
- Performance of urethanes
- UV resistance
- Ease Maintenance

- Non-Yellowing
- Water repellent
- Non-acidic
- Chemically Resistant

PRODUCTS

- S-9500 Color Stain
- SK-P250 Clear or
- SK-P250 Clear Satin or
- SK-P250 VOC Clear or
- SK-P250 VOC Clear Satin

SYSTEM USES

Interior/Exterior Concrete Commercial/Residential

Stamped Concrete Driveways Masonry Walls
Stamped Overlays Walkways Water Features

Art Deco Surfaces Pool Decks Anywhere Color is Desired

COLORS

Available in 20 standard colors. Please refer to the S-9500 Color Stain Color Chart.

PHYSICAL PROPERTIES	
7 Days at 75°F (24°C) Resin and Hardener	
Gloss (Satin clear gloss, 60 degrees) ASTM D523	90
Gloss (Satin material, 60 degrees)	50 - 60
Tensile Strength ASTM D882	8,000 psi
Tensile Elongation ASTM D882	10%
Flexibility ASTM D522 1/8 inch	Passes
Sward Hardness ASTM D2134	30
Pencil Hardness ASTM D3363	2H - 3H
Adhesion to Concrete ASTM D7234	300 psi
Abrasion Resistance ASTM D4060 (CS-17 wheel, 1 kg load, 1,000 cycles)	69 mg lost
Impact Resistance ASTM D2794 (160 inch-pounds direct and reversed)	Passes
Water Absorption ASTM D570 (24 hour immersion)	0.10 % maximum
Flammability ASTM D635 (Bonded to Concrete)	Self-Extinguishing
Microbial Resistant ASTM G21	Passes Rating #1

CHEMICAL RESISTANCE

Please refer to the Super-Krete Products Chemical Resistance Guide for system chemical resistance.

INSTALLATION

Please refer to the "Color Stain 250 System Application Instructions" for information on installing this system.





SYSTEM DATASHEET

Color Stain[™] 250 System

SPECIFICATION

Please refer to the "Color Stain 250 System Specification" for information on specifying this system.

MOISTURE VAPOR EMISSIONS PRECAUTIONS:

All concrete floors not poured over an effective moisture vapor retarder are subject to possible moisture vapor transmission that may lead to blistering and failure of the coating system. It is the coating applicator's responsibility to conduct calcium chloride testing in compliance with ASTM F1869, or relative humidity probe testing in compliance with ASTM-F2170, to determine if excessive levels of vapor emissions are present before applying any coatings. Arizona Polymer Flooring offers S-1300 Pene-Krete® for cementitious overlay products and VaporSolve® Moisture Remediation systems for resinous floor coatings. Consult our technical service department. Arizona Polymer Flooring and its sales agents will not be responsible for coating failures due to undetected moisture vapor emissions.

WARRANTY:

Arizona Polymer Flooring guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ARIZONA POLYMER FLOORING MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Arizona Polymer Flooring shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Arizona Polymer Flooring shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.



