# Color Stain<sup>™</sup> 5000 System

# SYSTEM DESCRIPTION

A water-based, penetrating, acrylic/urethane stain sealer with a two component, ultra high solids, VOC compliant, low viscosity, high chemical and abrasion resistant aliphatic polyurea/polyaspartic hybrid top coat. S-9500 Color Stain is translucent stain available in 20 standard colors, and provides a natural, fresh look for old as well as new surfaces, interior and exterior.

FEATURES & BENEFITS • Simple application • Performance of urethanes • UV resistance • Ease Maintenance		<ul> <li>Non-Yellowing</li> <li>Water repellent</li> <li>UV resistance</li> <li>Non-Acidic</li> <li>Chemically resistant</li> </ul>	PRODUCTS • S-9500 Color Stain • SK-P5000 Clear • SK-P5000 Clear (Fast Cure)
SYSTEM USES		Commercial/Residential	COLORS Available in 20 standard colors. Please refer to the S-9500 Color Stain
Stamped Concrete	Driveways	Masonry Walls	Color Chart.
Stamped Overlays	Walkways	Water Features	
Art Deco Surfaces	Pool Decks	Anywhere Color is Desired	

PHYSICAL PROPERTIES				
7 Days at 75°F (24°C) Resin and Hardener				
Gloss (Satin clear gloss, 60 degrees) ASTM D523	90			
Tensile Strength ASTM D882	8,500 psi			
Tensile Elongation ASTM D882	10%			
Flexibility ASTM D522 (1/8″)	Passes			
Sward Hardness ASTM D2134	30			
Pencil Hardness ASTM D3363	2H - 3H			
Adhesion to Concrete ASTM D7234	300 psi			
Abrasion Resistance ASTM D4060 (CS-17 wheel, 1 kg load, 1,000 cycles)	36 mg lost			
Impact Resistance ASTM D2794 (160 inch-pounds direct and reversed)	Passes			
Water Absorption ASTM D570 (24 hour immersion)	0.10 % maximum			
Flammability ASTM D635 (Bonded to Concrete)	Self-Extinguishing			

### CHEMICAL RESISTANCE

Please refer to the Super-Krete Products Chemical Resistance Guide for system chemical resistance.

### **INSTALLATION**

Please refer to the "Color Stain 5000 System Application Instructions" for information on installing this system.





# Color Stain<sup>™</sup> 5000 System

## **SPECIFICATION**

Please refer to the "Color Stain 5000 System Specification" for information on specifying this system.

## MOISTURE VAPOR EMISSIONS PRECAUTIONS:

All concrete floors not poured over an effective moisture vapor retarder are subject to possible moisture vapor transmission that may lead to blistering and failure of the coating system. It is the coating applicator's responsibility to conduct calcium chloride testing in compliance with ASTM F1869, or relative humidity probe testing in compliance with ASTM-F2170, to determine if excessive levels of vapor emissions are present before applying any coatings. Arizona Polymer Flooring offers **S-1300 Pene-Krete®** for cementitious overlay products and **VaporSolve®** Moisture Remediation systems for resinous floor coatings. Consult our technical service department. Arizona Polymer Flooring and its sales agents will not be responsible for coating failures due to undetected moisture vapor emissions.

### WARRANTY:

Arizona Polymer Flooring guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ARIZONA POLYMER FLOORING MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Arizona Polymer Flooring shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Arizona Polymer Flooring shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.



